

sub  
B1  
A

1. (Amended) A flat panel field emission display comprising:  
a screen having a phosphor coating;  
an emission source opposite said screen which selectively excites  
portions of said phosphor coating to generate visible light; and  
a black matrix provided on said screen, said black matrix being formed  
from praseodymium-manganese oxide.

2 sub  
B1  
A

10. (Amended) A flat panel field emission display, comprising:  
a faceplate including a screen, phosphors provided on said screen, and a  
black matrix provided on said screen;  
a baseplate assembly including a plurality of electron emission cathode  
tips arranged in an array and a low potential extraction grid;  
wherein said black matrix is formed from  $\text{PrMnO}_3$ .

Please add the following new claims 28-31:

3  
sub  
B1  
A

--28. The display of claim 1, wherein the praseodymium-manganese  
oxide has a high molar ratio of praseodymium to manganese.

29. The display of claim 1, wherein particles of the praseodymium-  
manganese oxide have an average size of 2 micrometers.